

CLAIMS

1. (withdrawn): A high contact angle char forming adherent comprising of:
 - i. a pseudo-nano particulate magnesium Alumino silicate;
 - ii. water in sufficient amounts to disperse said adherent to form a colloidal suspension of 5% to 19% by weight in water;
 - iii. a flocculating agent selected from water soluble salts containing: Na, Cl, K, Mg, Sr, Ca, Li, Br or SO₄ but optimally Epsom salt (magnesium sulfate) and when mixed with water soluble salts, will produce a eductable and sprayable composition from which a thickened char forming suspension is formed and will optionally include;
 - iv. an additive selected from the group consisting of carbonates, borates or phyllosilicates such as micas or vermiculite.
2. (withdrawn): A step-by-step process for making Acti-Quench by:
 - i. shear mixing between 5-19 percent formula weight of Acti-Quench with water to create a dispersion;
 - ii. mixing between 0.25-50 percent formula weight of a flocculant to the dispersion;
 - iii. mixing an ameliorative fire suppression and quenching additives to the dispersion;
 - iv. retaining the dispersion in a pumpable spray container and;

- v. discharging the dispersion from the container in a shear thinning spray action, whereby a sprayable high contact adherent temporary protective coating is formed.

3. (original): A composition useful for providing a fire protective coating on surfaces by immobilizing water therein and producing evaporative cooling comprising about 5-15% Attapulgitic clay, about 1-10% magnesium sulfate with water to make 100%.

4. (original): The composition of claim 3 wherein the composition comprises about 13.5-15% Attapulgitic clay, about 1% magnesium sulfate and the balance water to make 100%.

5. (currently amended): The composition of claim 3 wherein the Attapulgitic clay is purified micronized self-dispersing hydrous Attapulgitic clay.

6. (original): A method for preventing the advance of a fire and creating a fire-barrier comprising applying to the area to be protected from the advancing fire a fire-barrier composition comprising fire-barrier effective amounts of a composition of Attapulgitic clay, Epsom salt and water.

7. (original): The method of claim 6 wherein the fire-barrier composition comprises on a total weight basis 5-15% purified Attapulgitic clay, 1-15% Epsom salt and water to make 100%.

8. (currently amended): The method of claim 6 wherein the fire-barrier composition on a total weight basis comprises about 13.5 to 15% of micronized self-dispersing hydrous Attapulgitic clay, about 1% Epsom salt and about 85% of water.

Serial No.: 10/696,197
Docket No.: 03283-PA
Inventors: Parker et al

- 9 (original): The method of claim 6 wherein the composition applied to the area to be protected is a quarter of an inch or greater.
10. (original): The method of claim 6 wherein the area to be protected is around a land-fill.
11. (original): The method of claim 6 wherein the area to be protected is the area around burning tires.
12. (canceled).
13. (original): A method for fighting a fire comprising applying to said fire a composition of Attapulgate clay, Epsom salt and water in amounts effective to fight said fire.